

Aisi 4145 steel astm equivalent

aisi 4145 steel astm equivalent

Understanding the different grades of steel and their standards is essential for engineers, manufacturers, and procurement specialists. When it comes to AISI 4145 steel, one of the most common inquiries is its ASTM equivalent. Knowing the ASTM equivalent of AISI 4145 steel helps ensure compatibility, meet regulatory requirements, and select the right material for specific applications. This article provides a comprehensive overview of AISI 4145 steel, its properties, and its ASTM equivalents, offering valuable insights for professionals in the steel and manufacturing industries.

Introduction to AISI 4145 Steel

What is AISI 4145 Steel?

AISI 4145 steel is a chromium-molybdenum alloy steel known for its high strength, toughness, and excellent hardenability. It is commonly used in the manufacturing of components that require high tensile strength, wear resistance, and fatigue resistance, such as gears, shafts, and structural parts.

Main Characteristics of AISI 4145 Steel

- Chemical Composition:
 - Carbon (C): 0.43-0.50%
 - Chromium (Cr): 0.80-1.10%
 - Molybdenum (Mo): 0.20-0.30%
 - Manganese (Mn): 0.60-1.00%
 - Silicon (Si): 0.15-0.35%
 - Sulfur (S): Max 0.040%
 - Phosphorus (P): Max 0.040%
- Mechanical Properties:
 - High tensile strength
 - Good ductility
 - Excellent hardenability

- Heat Treatment: Suitable for various heat treatments like quenching and tempering to enhance specific properties.

- Applications: Used in manufacturing gears, shafts, axles, and other components requiring high strength and toughness.

ASTM Standards and Their Role

ASTM International develops and publishes technical standards for a wide range of materials, including steels. ASTM standards specify chemical compositions, mechanical properties, testing methods, and other criteria to ensure material quality and performance.

When selecting materials for critical applications, it is vital to identify ASTM equivalents to ensure compliance, compatibility, and optimal performance.

ASTM Equivalent Grades of AISI 4145 Steel

Understanding the Equivalence

Steel grades from different standards often have similar chemical compositions and mechanical properties but are designated differently. The ASTM standards most relevant to alloy steels like AISI 4145 include ASTM A29, ASTM A193, ASTM A320, and ASTM A105. However, for the specific chemical composition and mechanical properties of AISI 4145, the most common ASTM equivalent is ASTM A182 Grade F22.

Primary ASTM Equivalent: ASTM A182 Grade F22

- **ASTM A182 Grade F22**
 - Composition: Similar to AISI 4145, with comparable chromium and molybdenum content.
 - Application: Often used for high-temperature and high-pressure applications, such as flanges, valves, and fittings.
 - Properties: High strength, good toughness, and excellent hardenability.

Other Related ASTM Grades

While ASTM A182 F22 is the primary equivalent, other grades can sometimes serve as substitutes depending on specific requirements:

- **ASTM A29 4140 / 4145**

- This specification covers alloy steel bars, plates, and shapes.
- 4140 steels are similar but may have slight variations in chemical composition.

- **ASTM A193 Grade B7**

- Used primarily for fasteners, but shares some properties with 4145, especially after heat treatment.

- **ASTM A320 Grade L7**

- For low-temperature service applications, with similar alloying elements.

Note: Always verify chemical composition and mechanical properties before substituting grades to ensure suitability.

Comparison of Chemical Composition

Understanding the chemical composition helps determine the interchangeability of steel grades.

Element	AISI 4145 (%)	ASTM A182 F22 (%)	Remarks
-----	-----	-----	-----
Carbon (C)	0.43-0.50	0.20-0.30	Slightly higher in 4145, contributing to higher strength
Chromium (Cr)	0.80-1.10	1.00-1.50	Similar, with F22 sometimes having higher chromium for corrosion resistance
Molybdenum (Mo)	0.20-0.30	0.15-0.25	Similar, enhances hardenability
Manganese (Mn)	0.60-1.00	0.60-0.90	Comparable
Silicon (Si)	0.15-0.35	0.15-0.40	Similar

Implication: The chemical compositions are close enough for these grades to be used interchangeably in many applications, provided mechanical properties and heat treatments are also aligned.

Mechanical Properties and Heat Treatment

Typical Mechanical Properties

| Property | AISI 4145 | ASTM A182 F22 |

|-----|-----|-----|

| Tensile Strength | 850-1000 MPa | 690-930 MPa |

| Yield Strength | ~620 MPa | ~450 MPa |

| Hardness (after heat treatment) | Up to 50 HRC | Similar, depending on heat treatment |

Heat Treatment Processes

- Quenching and Tempering: Enhances hardness, strength, and toughness.
- Annealing: Improves ductility and machinability.
- Normalization: Refines grain structure for better toughness.

The heat treatment procedures are similar across grades, and the choice depends on the desired mechanical properties for specific applications.

Applications and Suitability of ASTM Equivalents

Knowing the ASTM equivalent of AISI 4145 steel is crucial when sourcing materials for projects requiring compliance with American standards. Below are typical applications where these grades are suitable:

- **High-Strength Components** ? Gears, shafts, and axles in automotive and industrial machinery.
- **Structural Parts** ? Structural steel in construction that demands high tensile strength.
- **Pressure Vessels and Piping** ? For high-pressure and high-temperature environments, especially when using ASTM A182 F22.
- **Oil and Gas Industry** ? Components exposed to harsh environments, benefiting from the alloy's toughness.

Choosing the right ASTM grade depends on:

- Mechanical property requirements
- Environmental conditions
- Specific standards compliance
- Cost considerations

Procurement and Quality Assurance

When procuring AISI 4145 steel or its ASTM equivalents, consider the following:

- **Certification:** Ensure the supplier provides proper mill test reports (MTRs) verifying chemical composition and mechanical properties.
- **Standards Compliance:** Confirm that the material meets relevant ASTM standards such as ASTM A182, A29, or A193.
- **Heat Treatment Documentation:** Verify heat treatment procedures and results to ensure material performance.
- **Inspection and Testing:** Conduct non-destructive testing (NDT), hardness testing, and chemical analysis if necessary.

Conclusion

In summary, the primary ASTM equivalent of AISI 4145 steel is ASTM A182 Grade F22, sharing similar chemical composition, mechanical properties, and applications. While other grades like ASTM A29 4140/4145 and ASTM A193 B7 can serve as substitutes depending on specific requirements, always verify compatibility through detailed specifications and testing. Understanding these equivalences ensures the right material selection, compliance with standards, and optimal performance in critical applications.

By thoroughly analyzing chemical compositions, mechanical properties, and intended uses, engineers and procurement specialists can confidently select the appropriate ASTM grade that aligns with the characteristics of AISI 4145 steel, ensuring safety, durability, and efficiency in their projects.

aisi 4145 steel astm equivalent ? this phrase encapsulates a vital link within the global steel industry, connecting a specific alloy to its standardized counterparts recognized across various standards organizations. Understanding this equivalence is crucial for engineers, manufacturers, and quality assurance professionals who rely on precise material specifications for safety, performance, and manufacturing efficiency. In this comprehensive review, we delve into the properties, applications, and ASTM equivalents of AISI 4145 steel, providing detailed insights that facilitate informed decision-making in industrial contexts.

Introduction to AISI 4145 Steel

Overview of AISI 4145 Steel

AISI 4145 is a low-alloy steel known for its high strength, toughness, and good wear resistance. It belongs to the family of 4000-series steels characterized by their alloying elements, primarily chromium and molybdenum, which enhance hardness, tensile strength, and overall durability.

This steel grade is often employed in applications requiring high fatigue strength and good machinability, such as gears, shafts, and components subjected to cyclic loads. Its composition strikes a balance between toughness and hardenability, making it a versatile choice for demanding engineering applications.

Key Properties of AISI 4145

- Chemical Composition:
 - Carbon (C): 0.43?0.50%
 - Manganese (Mn): 0.60?0.90%
 - Chromium (Cr): 0.80?1.10%
 - Molybdenum (Mo): 0.15?0.25%
 - Other elements in trace amounts, such as nickel and vanadium, may be present.
- Mechanical Properties:
 - Tensile strength: approximately 930?1100 MPa (135?160 ksi)
 - Yield strength: around 750 MPa (109 ksi)
 - Hardness after heat treatment: 248?302 HB
 - Toughness: High impact resistance suitable for cyclic loading.
- Heat Treatment:
 - Typically quenched and tempered to attain desired mechanical properties
 - Can be normalized or annealed depending on application requirements.

Understanding ASTM Standards and Material Classification

What are ASTM Standards?

ASTM International (originally the American Society for Testing and Materials) develops and publishes voluntary consensus technical standards for a wide range of materials, products, systems,

and services. For steels, ASTM provides specifications that define chemical composition, mechanical properties, testing methods, and manufacturing processes.

These standards ensure consistency, safety, and interchangeability of materials across different manufacturing and application sectors worldwide.

Significance of ASTM Equivalents

ASTM equivalents facilitate global commerce and manufacturing by enabling engineers and suppliers to specify materials without ambiguity. When a steel grade like AISI 4145 is referenced, identifying its ASTM equivalent ensures that the selected material meets the required standards for mechanical strength, chemical composition, and performance.

ASTM Equivalents of AISI 4145 Steel

Primary ASTM Specification for AISI 4145

The most relevant ASTM designation for AISI 4145 steel is ASTM A29 / A29M ? "Standard Specification for Steel Bars, Alloy, Standard Quality." Within this specification, AISI 4145 generally corresponds to ASTM A29 Grade 4145.

This grade covers alloy steel bars suitable for machining, forging, and heat treatment, with properties similar to those specified in AISI 4145.

Comparison of Chemical Composition

Element AISI 4145 ASTM A29 Grade 4145		
----- ----- -----		
Carbon (C)	0.43?0.50%	0.43?0.50%
Manganese (Mn)	0.60?0.90%	0.60?0.90%
Chromium (Cr)	0.80?1.10%	0.80?1.10%
Molybdenum (Mo)	0.15?0.25%	0.15?0.25%
Other elements	Trace	Trace

The close match in chemical composition indicates that ASTM A29 Grade 4145 is the primary ASTM

standard equivalent.

Mechanical and Heat Treatment Standards

ASTM A29 Grade 4145 specifies mechanical properties and heat treatment procedures similar to those outlined for AISI 4145 steel. This includes:

- Quenching and tempering to achieve specified hardness and strength
- Machinability requirements
- Testing procedures for tensile, hardness, and impact properties

Other Relevant ASTM Standards and Cross-References

While ASTM A29 Grade 4145 is the main equivalent, other standards may also be relevant depending on application specifics:

- ASTM A193 / A193M ? for alloy steel bolts and studs made from similar compositions
- ASTM A320 / A320M ? for alloy steel bolting materials, including 4145 variants

Manufacturers and engineers may reference these standards for specific components such as fasteners and fittings.

Global Material Standards and Cross-References

Comparison with Other International Standards

Apart from ASTM, several other standards organizations define equivalent grades for AISI 4145 steel, including:

- EN (European Norms): EN 10083-3 42CrMo4 (similar alloy steel)
- JIS (Japanese Industrial Standards): SNCM439 (chromium molybdenum steel)
- ISO Standards: ISO 683-2 42CrMo4

These grades share similar chemical compositions and mechanical properties, allowing for cross-reference in international procurement and engineering.

Summary of International Equivalents

| Standard | Grade | Composition Similarity | Typical Applications |

|-----|-----|-----|-----|

| ASTM A29 Grade 4145 | 4145 | High | Gears, shafts, structural components |

| EN 10083-3 42CrMo4 | 42CrMo4 | Very High | Heavy-duty machinery, automotive parts |

| JIS SNCM439 | SNCM439 | High | Gear wheels, axles, crankshafts |

| ISO 683-2 42CrMo4 | 42CrMo4 | Very High | Heavy equipment, machine parts |

Understanding these cross-references is vital for international projects, where compliance with multiple standards is required.

Applications and Suitability of AISI 4145 and Its ASTM Equivalent

Industrial Applications

AISI 4145 steel and its ASTM equivalent are prized for their mechanical strength, toughness, and heat treatment flexibility. Typical applications include:

- Gear manufacturing: high fatigue strength and wear resistance make it suitable for gear teeth and hubs.
- Shafts and axles: where high tensile strength and impact resistance are critical.
- Heavy machinery components: such as crankshafts, connecting rods, and pinions.
- Oil and gas industry: for drill bits and downhole tools due to toughness.

Advantages of Using ASTM Standards for Material Selection

- Global acceptance: ASTM standards are recognized worldwide, facilitating international trade.
- Consistent quality: specifications ensure uniform chemical composition and mechanical properties.
- Design confidence: engineers can rely on documented properties for safety margins.
- Ease of procurement: standardized grades simplify sourcing from multiple suppliers.

Limitations and Considerations

- Heat treatment variability: different heat treatment practices may lead to variations in properties.
- Manufacturing tolerances: adherence to ASTM tolerances is critical for performance.
- Material availability: not all suppliers may stock ASTM Grade 4145, requiring careful specification.

Conclusion and Future Outlook

The equivalence between AISI 4145 steel and ASTM A29 Grade 4145 underscores the importance of standardization in the global steel industry. Recognizing these standards enables engineers and manufacturers to select appropriate materials with confidence, ensuring performance, safety, and interoperability.

As industries evolve, so too will material standards, with increased emphasis on sustainability, advanced heat treatments, and alloy innovations. Continuous research aims to enhance the properties of low-alloy steels like 4145, expanding their applications and improving their manufacturing processes.

In conclusion, whether specified by AISI, ASTM, or international standards, AISI 4145 steel remains a vital alloy in heavy-duty engineering applications, with ASTM equivalents providing a reliable reference framework for global procurement and engineering design. Understanding these equivalences is essential for achieving optimal performance in demanding industrial environments.

References

- ASTM International Standards
- AISI Steel Data Sheets
- European Norms (EN) Specifications
- JIS Steel Standards
- Industry Publications on Alloy Steels
- Technical Guides on Heat Treatment and Mechanical Testing

Question What is the ASTM equivalent of AISI 4145 steel? The ASTM equivalent of AISI 4145 steel is ASTM A29 4145H, which is a high-strength alloy steel used for similar applications. **What are the main properties of AISI 4145 steel that are reflected in its ASTM equivalent?** Both AISI 4145 and its ASTM equivalent possess high tensile strength, toughness, and good wear resistance, making them suitable for heavy-duty applications such as gears and shafts. **Is AISI 4145 steel the same as ASTM 4145H?** While both are similar, ASTM 4145H specifically refers to a high-strength, quenched and tempered grade of 4145 steel, aligning with AISI 4145's properties, but always verify specific requirements for your application. **Can AISI 4145 steel be substituted with ASTM 4145H in manufacturing?** Yes, ASTM 4145H is considered an equivalent and can generally be substituted for

AISI 4145 steel in manufacturing, provided specifications and heat treatment processes are matched. What are the typical applications of AISI 4145 steel and its ASTM equivalent? Both are commonly used in the manufacturing of gears, shafts, and other components requiring high strength, toughness, and wear resistance. Where can I find more detailed chemical composition and mechanical properties of ASTM 4145H? Detailed information can be found in ASTM A29 standards and material datasheets, which provide comprehensive chemical and mechanical property data for ASTM 4145H steel.

Related keywords: aisi 4145 steel, astm 4145, 4145 alloy steel, 4145 steel properties, 4145 steel hardness, astm alloy standards, alloy steel grades, 4145 steel composition, heat treatable steel, alloy steel specifications

Ms 4361 steel equivalent

ms 4361 steel equivalent

ms 4361 steel equivalent is a critical consideration in the manufacturing, engineering, and construction industries where material selection influences the durability, strength, and performance of products. MS 4361 is a standard designation used primarily in certain regions, notably India, to specify a particular grade of steel with defined chemical composition and mechanical properties. Understanding its equivalents is essential for engineers, procurement specialists, and manufacturers who seek to source alternative materials that meet the same standards and performance criteria. This comprehensive guide explores the details of MS 4361 steel, its properties, and its international equivalents to facilitate informed decision-making in various industrial applications.

What is MS 4361 Steel?

MS 4361 is a standard specification for a specific grade of medium carbon steel. It is primarily used in manufacturing mechanical parts, shafts, gears, and other components requiring good strength, toughness, and wear resistance. The steel grade is characterized by its chemical composition, hardness, and mechanical properties, which make it suitable for applications demanding high strength and durability.

Chemical Composition of MS 4361 Steel

The typical chemical composition of MS 4361 steel includes:

- Carbon (C): 0.40% ? 0.60%
- Manganese (Mn): 0.60% ? 1.00%
- Silicon (Si): Up to 0.40%
- Phosphorus (P): Up to 0.025%
- Sulfur (S): Up to 0.035%

The specific composition may vary slightly depending on the manufacturer and application requirements. The steel's carbon content imparts hardness and strength, while manganese enhances hardenability and toughness.

Mechanical Properties

- Tensile strength: Generally ranges from 370 MPa to 600 MPa
- Hardness: Typically around 170-210 HB (Brinell Hardness)
- Toughness: Good impact resistance when properly heat-treated
- Ductility: Moderate, suitable for machining and forming processes

Applications of MS 4361 Steel

MS 4361 steel is widely used in manufacturing:

- Shafts and axles
- Gears and pinions
- Mechanical parts subjected to wear and fatigue
- Forgings and machined components
- Agricultural and construction machinery parts

Its combination of strength, toughness, and machinability makes it a versatile choice for various industrial applications.

Why Knowing MS 4361 Steel Equivalents Is Important

Understanding the equivalents of MS 4361 steel is crucial for several reasons:

- Cost Optimization: Sourcing alternative steels with similar properties can reduce manufacturing costs.
- Global Procurement: When importing materials, knowing international equivalents ensures compatibility and compliance.

- Design Flexibility: Engineers can select from a broader range of materials without compromising performance.
- Availability: Sometimes, MS 4361 steel may have limited availability; knowing equivalents helps maintain production schedules.

International Equivalents of MS 4361 Steel

Different countries and standards organizations define similar steels with varying designations. Here's an overview of some common equivalents:

- ASTM (American Society for Testing and Materials) Equivalents

Standard	Steel Grade	Composition & Properties
----------	-------------	--------------------------

-----	-----	-----
-------	-------	-------

ASTM A29	1045	Medium carbon steel with similar carbon content, good strength, and machinability
----------	------	---

ASTM A193	Grade B7	High-strength alloy steel, used in fasteners and high-temperature applications (for comparison)
-----------	----------	---

- SAE (Society of Automotive Engineers) / AISI (American Iron and Steel Institute)

Grade	Corresponding Steel	Notes
-------	---------------------	-------

-----	-----	-----
-------	-------	-------

SAE 1045	AISI 1045	Similar medium carbon steel, widely used in mechanical parts, shafts, gears
----------	-----------	---

- European Standards (EN)

Standard	Steel Grade	Equivalent Type	Notes
----------	-------------	-----------------	-------

-----	-----	-----	-----
-------	-------	-------	-------

EN 10083-2	42CrMo4	Alloy steel with similar strength and toughness, often used as an
------------	---------	---

alternative in high-stress components |

| EN 10083-1 | C45 | Medium carbon steel with comparable properties |

- JIS (Japanese Industrial Standards)

| Standard | Steel Grade | Equivalent | Notes |

|-----|-----|-----|-----|

| JIS G4051 | S45C | Similar medium carbon steel, used in machinery components |

How to Select the Right Equivalent Steel

When choosing an equivalent to MS 4361 steel, consider the following factors:

- Chemical Composition: Ensure the alloying elements match required specifications.
- Mechanical Properties: Tensile strength, hardness, toughness, and ductility should meet application demands.
- Heat Treatment Capabilities: Compatibility with heat treatment processes like quenching and tempering.
- Standards Compliance: Verify that the alternative steel complies with relevant standards for the intended application.
- Availability and Cost: Consider the local availability and cost implications.

Heat Treatment and Machinability of MS 4361 and Its Equivalents

Proper heat treatment enhances the mechanical properties of MS 4361 steel and its equivalents. Common heat treatment processes include:

- Normalization: Refines grain size and improves toughness.
- Quenching and Tempering: Increases strength and hardness while maintaining toughness.
- Carburizing: Surface hardening for wear resistance.

Machinability is generally moderate for MS 4361 and equivalent steels like 1045 or C45, making them suitable for machining operations such as turning, milling, and drilling.

Benefits of Using Steel Equivalents

- Flexibility in sourcing materials based on regional availability.
- Cost savings by choosing more economical options.
- Consistent performance when equivalents meet the same standards.
- Simplified procurement processes through knowledge of international standards.

Conclusion

Understanding the **MS 4361 steel equivalent** is essential for industries that rely on medium carbon steels for manufacturing critical components. While MS 4361 offers an excellent balance of strength, toughness, and machinability, its equivalents like ASTM 1045, JIS S45C, and European 42CrMo4 provide similar properties suitable for various applications worldwide. Selecting the right steel involves a thorough comparison of chemical composition, mechanical properties, heat treatment capabilities, and standards compliance.

By leveraging knowledge of these equivalents, engineers, procurement managers, and manufacturers can optimize costs, ensure material availability, and maintain product quality across global markets. Whether sourcing locally or internationally, understanding these standards ensures that the materials used meet the stringent demands of modern engineering and manufacturing.

Additional Resources

- Steel Standards and Specifications: Consult relevant standards organizations such as ASTM, JIS, EN, and IS for detailed specifications.
- Material Testing: Always perform mechanical and chemical testing to confirm material properties before use.
- Consult Suppliers: Engage with reputable steel suppliers for guidance on material grades and certifications.

In summary, mastering the concept of MS 4361 steel and its equivalents enables better decision-making in material selection, ensuring that components and structures perform reliably throughout their service life.

MS 4361 steel equivalent is a term that resonates deeply within the engineering, manufacturing, and materials science sectors, as it pertains to identifying steels with similar properties, compositions, and performance characteristics. As industries worldwide demand high-performance materials tailored to specific applications—from construction and automotive to aerospace and machinery—the importance of understanding steel equivalents like MS 4361 becomes paramount. This comprehensive review aims to elucidate the nature of MS 4361 steel, explore its chemical and mechanical properties, identify its international equivalents, and analyze their comparative advantages and limitations.

Understanding MS 4361 Steel

Definition and Origin

MS 4361 is a designation used primarily within the Indian standards system, particularly under the Bureau of Indian Standards (BIS). It refers to a specific grade of medium-carbon steel that is characterized by its strength, toughness, and weldability. The designation "MS" stands for "Mild Steel," though MS 4361 is more accurately classified as a medium carbon steel, often used for manufacturing components that require moderate strength and ductility.

The standard MS 4361 specifies chemical composition, mechanical properties, and permissible variations, providing manufacturers and engineers with a reliable reference point for material selection. Since the BIS standards are rooted in national requirements, they often align with or are comparable to international standards such as ASTM, EN, or JIS, leading to the development of equivalent grades across different standards.

Applications of MS 4361 Steel

MS 4361 steel finds extensive application in various sectors owing to its balanced properties:

- Automotive Components: shafts, gears, and axles requiring toughness and moderate strength.
- Structural Parts: bolts, nuts, and fasteners in construction projects.
- Machinery Parts: shafts and spindles subjected to moderate loads.
- Agricultural Equipment: plows, tines, and other parts exposed to wear.

Its popularity stems from its ease of welding, machinability, and cost-effectiveness, making it an ideal choice for medium-duty applications.

Chemical Composition and Mechanical Properties of MS 4361

Chemical Composition

The chemical makeup of MS 4361 steel typically includes the following elements (approximate ranges):

- Carbon (C): 0.30% ? 0.40%
- Manganese (Mn): 0.60% ? 0.90%
- Sulfur (S): ? 0.05%
- Phosphorus (P): ? 0.05%

- Other Elements: minor traces of silicon, nickel, chromium, and molybdenum may be present in small quantities.

The carbon content is a critical factor influencing the hardness, strength, and weldability of the steel.

Mechanical Properties

Based on the standard specifications, MS 4361 exhibits the following typical mechanical properties:

- Yield Strength: approximately 300 MPa (megapascals)
- Tensile Strength: around 480-620 MPa
- Elongation: 20% - 25% in 50 mm gauge length
- Hardness: approximately 120-180 HB (Brinell Hardness)
- Impact Toughness: suitable for moderate impact loads

These properties make MS 4361 a versatile material, suitable for moderate to high-stress components, especially where good weldability is imperative.

International Equivalents of MS 4361 Steel

Given the widespread use of steel grades across different regions, understanding the equivalents of MS 4361 within international standards is essential for global manufacturing and procurement. Equivalence is generally established based on chemical composition, mechanical properties, and processing characteristics.

ASTM (American Society for Testing and Materials) Equivalents

The most comparable ASTM grade to MS 4361 is:

- ASTM A36 Steel

Key Similarities:

- Carbon content ranges from 0.26% to 0.29%, close to MS 4361.
- Tensile strength of 400-550 MPa.
- Good weldability and machinability.

Differences:

- Slight variations in chemical composition, especially in manganese and sulfur content.
- ASTM A36 is often considered a mild steel, but its properties align closely with MS 4361 for general purposes.

Other ASTM Grades:

- ASTM A572 Grade 50: offers higher strength but different chemical makeup.
- ASTM A529 Grade 50: similar in mechanical properties but with specific chemical variations.

European (EN) Standards Equivalents

Within the EN (European Norm) system, the following grades are comparable:

- EN 10025 S235JR

Details:

- Structural steel with yield strength of 235 MPa.
- Similar chemical composition, with controlled amounts of carbon, manganese, and other elements.
- Widely used in construction and structural applications.

Note: While S235JR has a lower yield strength than MS 4361, in terms of chemical composition and general mechanical behavior, it is considered an equivalent for many applications.

Japanese (JIS) Standards Equivalents

- JIS G3101 SS400

Features:

- Similar chemical composition with carbon around 0.16%?0.20%.
- Tensile strength of approximately 400?510 MPa.
- Widely used in construction and general engineering.

Other Notable Equivalents

Standard	Grade	Approximate Chemical Composition	Mechanical Properties	Remarks
-----	-----	-----	-----	-----
ASTM	A36	C: 0.26?0.29%, Mn: 0.60?0.90%	Tensile: 400?550 MPa	Widely used, versatile
EN	S235JR	C: 0.17?0.20%, Mn: 1.40?1.70%	Tensile: 370?510 MPa	Suitable for structural work
JIS	SS400	C: 0.16?0.20%, Mn: 1.20?1.60%	Tensile: 400?510 MPa	Good weldability

Comparative Analysis of MS 4361 and Its Equivalents

Chemical Composition Variations

While the grades listed as equivalents share similar chemical compositions, subtle differences can influence their performance:

- Carbon Content: Slightly lower in some standards (like JIS SS400) which can result in reduced strength but enhanced weldability.
- Manganese: Variations can affect hardenability and tensile strength.
- Sulfur and Phosphorus: Kept minimal across all grades to ensure ductility and weldability.

Mechanical Properties and Performance

In general, the mechanical properties of these equivalents are comparable, with tensile strengths around 400?550 MPa and yield strengths near 235?300 MPa. However, specific application requirements may necessitate choosing a grade with higher or lower properties.

Weldability and Machinability

All grades exhibit good weldability, but higher carbon contents or alloying elements may require preheating or post-weld heat treatments. MS 4361 and ASTM A36 are renowned for their ease of welding, making them suitable for fabrication.

Cost and Availability

- MS 4361: Readily available in India and neighboring regions, often at a cost-effective rate.
- ASTM A36: Widely available globally, often at competitive prices.

- EN S235JR and JIS SS400: Common in Europe and Japan, respectively, with good supply chains.

Considerations When Selecting an Equivalent Steel

Choosing the appropriate steel grade requires a nuanced understanding of application-specific parameters:

- Mechanical Requirements: Tensile strength, yield strength, toughness.
- Weldability: Ease of welding, susceptibility to cracking.
- Corrosion Resistance: Not typically a concern for MS 4361 unless specified.
- Cost and Availability: Local supply chains and procurement costs.
- Standards Compliance: Ensure that the chosen grade meets project specifications and standards.

Conclusion and Final Thoughts

The term MS 4361 steel equivalent encapsulates a critical aspect of materials engineering: the ability to identify and utilize alternative materials that match specific performance criteria. Recognizing the equivalent grades—such as ASTM A36, EN S235JR, and JIS SS400—enables engineers and manufacturers to optimize sourcing, reduce costs, and ensure quality across international projects.

While these grades share core similarities, it remains essential to analyze their detailed chemical compositions and mechanical properties in relation to the intended application. Factors like weldability, machinability, and environmental conditions influence the final selection.

In a globalized manufacturing landscape, understanding steel equivalencies like MS 4361 not only facilitates seamless material interchange but also fosters innovation and efficiency. As industries evolve, ongoing research and standardization efforts will continue to refine these equivalences, ensuring that materials meet the demanding needs of modern engineering.

Key Takeaways:

- MS 4361 is a medium-carbon steel primarily used in India, with properties suitable for general engineering applications.
- International equivalents like ASTM A36, EN S235JR, and JIS SS400 offer comparable performance.
- Material selection should consider chemical composition, mechanical

QuestionAnswer What is the equivalent of MS 4361 steel in other international standards? MS 4361 steel is primarily equivalent to ASTM A283 Grade C and similar low to medium carbon steels used in structural applications. Can MS 4361 steel be replaced with standard ASTM steels for structural purposes? Yes, MS 4361 steel can often be replaced with ASTM A283 Grade C, but it's essential to verify mechanical properties and specifications before substitution. What are the key properties of MS 4361 steel compared to its equivalents? MS 4361 steel exhibits moderate tensile strength, good weldability, and corrosion resistance, similar to ASTM A283 Grade C, making it suitable for structural applications. Is MS 4361 steel suitable for structural engineering projects? Yes, MS 4361 steel is commonly used in structural engineering due to its strength and weldability, and it is often considered equivalent to ASTM A283 Grade C. How do I determine the chemical composition of MS 4361 steel and its equivalents? Refer to the official standards documents for MS 4361 and ASTM A283 Grade C to compare chemical compositions, focusing on carbon, manganese, phosphorus, sulfur, and other alloying elements. Are there any differences in mechanical properties between MS 4361 steel and its equivalents? While they are similar, slight variations may exist; always check specific grade datasheets to ensure mechanical properties meet your project requirements. Where can I find certified suppliers for MS 4361 steel and its equivalents? Certified steel suppliers and distributors specializing in structural steels can provide MS 4361 and equivalent grades like ASTM A283 Grade C; consult local steel standards organizations for recommendations.

Related keywords: MS 4361 steel, steel grade MS 4361, equivalent to ASTM steel, MS 4361 properties, MS 4361 hardness, MS 4361 composition, steel standards MS 4361, MS 4361 comparison, alloy MS 4361, steel grade equivalents

Aisi 4145 yield strength

aisi 4145 yield strength is a critical property that determines the performance and applicability of this versatile alloy steel. Understanding the yield strength of AISI 4145 is essential for engineers, manufacturers, and material scientists who utilize this alloy in various demanding applications. This article provides an in-depth analysis of AISI 4145's yield strength, including its composition, mechanical properties, heat treatment effects, and practical applications, all structured to optimize SEO relevance and readability.

What is AISI 4145 Steel?

AISI 4145 is a medium alloy steel categorized under the American Iron and Steel Institute (AISI) standards. It is primarily known for its excellent toughness, strength, and wear resistance. Typically,

AISI 4145 contains the following chemical composition:

- Carbon (C): 0.43?0.50%
- Manganese (Mn): 0.75?1.00%
- Chromium (Cr): 0.80?1.10%
- Molybdenum (Mo): 0.15?0.25%
- Other elements: Small quantities of sulfur and phosphorus

This composition results in a steel that offers a good balance of strength, toughness, and machinability, making it suitable for various industrial applications.

Understanding Yield Strength in Steel

Yield strength refers to the stress at which a material begins to deform plastically. Beyond this point, the material will not return to its original shape when the load is removed. It is a crucial parameter for designing components that must withstand specific loads without permanent deformation.

Key points about yield strength:

- It is measured in units of pressure, typically MPa (megapascal).
- It indicates the maximum stress a material can endure while still behaving elastically.
- Higher yield strength often signifies a stronger, more durable material.

Yield Strength of AISI 4145 Steel

The yield strength of AISI 4145 varies significantly depending on its heat treatment and manufacturing process. Below are typical values:

- **Normalized Condition:** Approximately 415?550 MPa
- **Hardened and Tempered Condition:** Can exceed 700 MPa
- **Cold Drawn or Machined Forms:** May have higher yield strengths due to work hardening

Note: These values are approximate and can vary based on specific processing and testing conditions.

Factors Affecting Yield Strength

Several factors influence the yield strength of AISI 4145, including:

- **Heat Treatment:** Quenching and tempering significantly enhance yield strength.
- **Cold Working:** Processes like cold drawing or rolling increase yield strength through work hardening.
- **Microstructure:** Fine grain structures tend to improve yield strength.
- **Alloying Elements:** Elements like chromium and molybdenum contribute to strength and hardness.

Heat Treatment and Its Impact on Yield Strength

Heat treatment processes are crucial for optimizing the yield strength of AISI 4145 steel. The common heat treatment methods include:

Normalizing

- Heating the steel to a temperature just above the critical point (around 850°C).
- Air cooling to refine grain structure.
- Results in moderate strength with improved toughness.

Quenching and Tempering

- Heating the steel to austenitizing temperature (~850°C).
- Rapid cooling in oil or water (quenching) to induce martensitic microstructure.
- Subsequent tempering at lower temperatures (around 550-700°C) to reduce brittleness and enhance toughness.
- This process significantly increases yield strength, often reaching above 700 MPa.

Cold Working

- Mechanical deformation at room temperature.
- Work hardening increases yield strength but may reduce ductility.

Summary Table: Effect of Heat Treatment on Yield Strength

Treatment Type	Typical Yield Strength (MPa)	Microstructure	Suitability
Normalized	415-550	Fine ferrite and pearlite	General purpose, moderate strength

| Quenched & T tempered | >700 | Martensite + tempered microstructure | High strength, wear resistance |

| Cold Worked | Varies (up to 800+) | Work-hardened microstructure | High strength, reduced ductility |

Mechanical Properties of AISI 4145 Steel

Apart from yield strength, other mechanical properties include:

- Ultimate Tensile Strength (UTS): 700-900 MPa after heat treatment
- Hardness: Up to 300 HB (Brinell Hardness) in hardened and tempered state
- Ductility: Moderate, decreases with increased strength
- Impact Toughness: Good in normalized condition, can be affected by high hardness levels

These properties make AISI 4145 suitable for applications requiring a combination of strength and toughness.

Applications of AISI 4145 Steel

The high yield strength and toughness of AISI 4145 make it ideal for various demanding applications, including:

- Gear manufacturing and shafts
- Power transmission components
- Structural components subjected to cyclic loads
- Oil and gas industry components, such as drill collars
- Heavy machinery parts that require high strength and durability

The ability to tailor the yield strength through heat treatment enhances its versatility in different engineering scenarios.

Testing and Certification of Yield Strength

Accurate measurement of yield strength is essential for ensuring safety and performance. Common testing methods include:

- **Tensile Testing:** Standard method involving applying uniaxial load until failure.

- **Rockwell Hardness Test:** Indirect correlation with yield strength.
- **Ultrasonic Testing:** Non-destructive evaluation for microstructural integrity.

Material suppliers often provide certified test reports specifying the yield strength based on standardized testing protocols.

Summary and Key Takeaways

- The aisi 4145 yield strength is highly dependent on processing and heat treatment, ranging from approximately 415 MPa in normalized conditions to over 700 MPa in quenched and tempered forms.
- Proper heat treatment enhances yield strength, making AISI 4145 suitable for high-stress applications.
- Mechanical properties such as tensile strength, hardness, and toughness complement its yield strength, providing a comprehensive performance profile.
- Its versatility and robust mechanical properties make AISI 4145 a preferred choice in industries demanding high strength, toughness, and wear resistance.

Conclusion

Understanding the yield strength of AISI 4145 is fundamental for optimizing its use in engineering and manufacturing. By carefully selecting heat treatment processes and controlling manufacturing variables, engineers can achieve the desired balance of strength, toughness, and ductility. Whether for critical structural components, gears, or heavy machinery parts, AISI 4145's yield strength characteristics ensure reliable and durable performance in demanding environments.

For best results, always consult the latest material datasheets and testing standards, and work with reputable suppliers to ensure the steel's properties meet your specific application requirements.

AISI 4145 Yield Strength: An Expert Analysis

When it comes to selecting the right alloy steel for demanding industrial applications, understanding the mechanical properties—particularly yield strength—is crucial. Among the various grades available, AISI 4145 stands out for its exceptional toughness, strength, and versatility. This article provides a comprehensive examination of AISI 4145's yield strength, exploring its composition, mechanical properties, heat treatment effects, applications, and how it compares with similar alloys.

Introduction to AISI 4145 Steel

AISI 4145 is a chromium-molybdenum alloy steel classified under the AISI (American Iron and Steel Institute) standards. It is known for its high strength, toughness, and wear resistance, making it

suitable for a wide range of high-stress applications. This alloy is often used in manufacturing components such as gears, shafts, axles, and power transmission equipment.

Composition and Characteristics

The typical chemical composition of AISI 4145 includes:

- Carbon (C): 0.43?0.50%
- Chromium (Cr): 0.80?1.10%
- Molybdenum (Mo): 0.15?0.25%
- Manganese (Mn): 0.60?1.00%
- Sulfur (S): Max 0.035%
- Phosphorus (P): Max 0.035%

This specific composition imparts AISI 4145 with excellent tensile strength, toughness, and hardenability, which are essential for high-performance applications.

Understanding Yield Strength in AISI 4145

What Is Yield Strength?

Yield strength is a fundamental mechanical property that indicates the maximum stress a material can withstand without undergoing permanent deformation. It essentially marks the transition point where the material stops behaving elastically and begins to deform plastically.

For steel alloys like AISI 4145, the yield strength is critical in design and engineering, ensuring that components can sustain operational loads without failure or significant deformation.

Typical Yield Strength Values for AISI 4145

The yield strength of AISI 4145 varies depending on heat treatment, manufacturing processes, and testing conditions. Broadly, the typical yield strength ranges are as follows:

- Normalized Condition: Around 50,000 to 70,000 psi (345 to 483 MPa)
- Hardened and Tempered Condition: Can reach 90,000 to 130,000 psi (620 to 895 MPa)

These figures are approximate and can differ based on specific processing parameters.

Factors Influencing Yield Strength of AISI 4145

Understanding what influences the yield strength of AISI 4145 is essential for optimizing its performance in various applications.

Heat Treatment Processes

Heat treatment significantly alters the mechanical properties, including yield strength:

- Normalization: Heating to austenitizing temperature followed by air cooling refines the grain structure, providing a balanced combination of strength and toughness.
- Quenching and Tempering: Quenching from high temperatures followed by tempering enhances hardness and yield strength. Tempering reduces brittleness while maintaining elevated strength levels.
- Carburizing: Surface hardening process that increases surface yield strength for wear resistance applications.

Mechanical Working and Cold Working

Processes such as forging, rolling, or machining at room temperature can induce strain hardening, thereby increasing yield strength.

Alloying Elements and Microstructure

Chromium and molybdenum contribute to the alloy's strength and hardenability, influencing the yield strength after heat treatments. Microstructure?such as martensitic or bainitic phases?also plays a significant role.

Measuring and Testing Yield Strength in AISI 4145

Standard Testing Methods

Yield strength is typically measured via standardized tensile tests, following ASTM E8/E8M guidelines. These tests involve:

- Applying uniaxial tensile load to a specimen
- Recording the stress-strain response
- Identifying the offset yield point (commonly 0.2% strain offset)

Practical Considerations

In real-world applications, factors such as residual stresses, surface treatments, and manufacturing imperfections can influence the measured yield strength, necessitating conservative design margins.

Applications of AISI 4145 Based on Yield Strength

The high yield strength of AISI 4145 makes it suitable for applications where strength, toughness, and wear resistance are critical.

Key Industries and Components

- Power Generation: Shafts, gears, and turbine blades that require high fatigue strength.
- Automotive: Drive shafts, axles, and high-stress transmission components.
- Oil & Gas: Drilling tools and piping subjected to high pressure and stress.
- Aerospace: Structural components demanding high strength-to-weight ratio.
- Military & Defense: Heavy-duty machinery and weapon components.

Benefits in Application

- Enhanced load-bearing capacity
- Improved fatigue life
- Resistance to impact and shock loading
- Good machinability post heat treatment

Comparative Analysis: AISI 4145 vs Other Alloy Steels

Understanding how AISI 4145 compares with similar alloys helps in making informed material choices.

Property	AISI 4145	AISI 4340	AISI 4140
Composition	Cr-Mo alloy	Cr-Mo-Ni alloy	Cr-Mo alloy
Typical yield strength (hardened)	90,000?130,000 psi	110,000?140,000 psi	75,000?100,000 psi
Toughness	Excellent	Very good	Good

| Hardness after heat treatment | Up to 55 HRC | Up to 55 HRC | Up to 55 HRC |

While AISI 4145 offers a balanced combination of strength and toughness, specific applications may favor other alloys depending on factors like weldability, machinability, and cost.

Design Considerations and Best Practices

When utilizing AISI 4145 in engineering designs, several factors should be considered:

- Heat Treatment Optimization: Tailoring heat treatment processes to achieve desired yield strength without compromising toughness.
- Residual Stresses: Minimizing residual stresses through proper machining and post-process treatments.
- Material Certification: Ensuring the material meets industry standards and specifications for critical applications.
- Corrosion Resistance: While AISI 4145 offers good mechanical properties, it may require surface treatments or coatings for corrosion-prone environments.

Safety Margins and Factor of Safety

Given the variability in yield strength depending on processing, engineers should incorporate appropriate safety factors?typically ranging from 1.5 to 3?to account for uncertainties.

Conclusion

AISI 4145 is a robust and versatile alloy steel, renowned for its high yield strength, toughness, and wear resistance. Its yield strength, which can range from approximately 50,000 psi in normalized conditions to over 130,000 psi when fully hardened and tempered, makes it suitable for high-stress components across various industries.

Understanding the factors that influence its yield strength?such as heat treatment, microstructure, and mechanical working?is vital for optimizing performance and ensuring safety and longevity in service. Whether used in power generation, automotive, or aerospace applications, AISI 4145 continues to be a preferred choice for engineers seeking a reliable, high-strength alloy steel solution.

By carefully selecting processing parameters and adhering to best design practices, engineers can leverage the impressive yield strength of AISI 4145 to create durable, efficient, and safe components for demanding applications.

Question What is the typical yield strength of AISI 4145 alloy steel? The typical yield strength of AISI 4145 alloy steel ranges from 65,000 to 90,000 psi (450 to 620 MPa), depending on the heat treatment and condition. How does heat treatment affect the yield strength of AISI 4145? Heat treatment processes such as quenching and tempering can significantly increase the yield strength of AISI 4145 by refining the microstructure and inducing martensitic or tempered martensitic phases, resulting in higher strength levels. Is AISI 4145 suitable for high-stress applications? Yes, due to its high yield strength and toughness, AISI 4145 is suitable for high-stress applications such as gear manufacturing, shafts, and pressure vessels, especially when properly heat-treated. How does alloying in AISI 4145 influence its yield strength? The alloying elements like chromium, molybdenum, and manganese in AISI 4145 enhance its hardenability and strength, contributing to higher yield strength and improved mechanical properties after heat treatment. What are the common heat treatment conditions to optimize the yield strength of AISI 4145? Common heat treatments include quenching in oil or air followed by tempering at 400-600°C, which optimize the microstructure for maximum yield strength while maintaining toughness. How does the yield strength of AISI 4145 compare to other alloy steels? AISI 4145 generally exhibits higher yield strength than lower-alloy steels like AISI 4140, especially after appropriate heat treatment, making it suitable for more demanding applications requiring enhanced mechanical performance.

Related keywords: aisi 4145 yield strength, alloy steel properties, 4145 steel mechanical properties, aisi 4145 tensile strength, 4145 steel hardness, alloy steel yield point, 4145 steel tensile test, aisi 4145 ductility, 4145 steel applications, alloy steel composition

Aisi 4130 properties

aisi 4130 properties make it a highly sought-after alloy in various engineering and manufacturing sectors due to its exceptional strength, toughness, and weldability. As a versatile chromium-molybdenum alloy steel, AISI 4130 combines excellent mechanical properties with good corrosion resistance, making it ideal for applications ranging from aerospace components to automotive parts and structural tubing. In this comprehensive guide, we explore the detailed properties of AISI 4130, its composition, advantages, applications, and treatment options to help engineers, manufacturers, and hobbyists understand its full potential.

Understanding AISI 4130 Steel

AISI 4130, also known as Chromoly or Cr-Mo steel, belongs to the family of low alloy steels. It is characterized by its high strength-to-weight ratio, good weldability, and excellent toughness. These properties are derived from its specific chemical composition and heat treatment processes, which can be tailored to meet diverse application requirements.

Chemical Composition of AISI 4130

The chemical makeup of AISI 4130 steel is carefully controlled to ensure its desirable properties. The typical composition includes:

- Carbon (C): 0.28% - 0.33%
- Chromium (Cr): 0.80% - 1.10%
- Molybdenum (Mo): 0.15% - 0.25%
- Iron (Fe): Balance
- Other elements (e.g., manganese, silicon, sulfur, phosphorus): Trace amounts

This specific combination imparts high tensile strength, good hardenability, and corrosion resistance, making AISI 4130 suitable for high-performance applications.

Mechanical Properties of AISI 4130

The mechanical characteristics of AISI 4130 can vary depending on heat treatment and processing but generally include:

Key Mechanical Properties:

- Ultimate Tensile Strength (UTS): 70,000 ? 90,000 psi (approx. 480 ? 620 MPa)
- Yield Strength (YS): 40,000 ? 70,000 psi (approx. 275 ? 480 MPa)
- Elongation: 20% ? 25% in 2 inches (50 mm)
- Hardness (after heat treatment): 170 ? 270 HB (Brinell hardness)
- Impact Toughness: High, especially in normalized and tempered conditions

These properties make AISI 4130 a reliable choice for load-bearing structures and components subjected to dynamic stresses.

Heat Treatment and Fabrication

One of the notable features of AISI 4130 is its excellent weldability and ability to undergo various heat treatments to enhance specific properties.

Heat Treatment Processes:

- **Normalizing:** Refines grain structure, improves toughness, and relieves internal stresses.

- **Quenching and Tempering:** Increases strength and hardness while maintaining toughness. Typically involves heating to austenitizing temperature, quenching in oil or air, followed by tempering.
- **Stress Relieving:** Reduces residual stresses after welding or fabrication.

Proper heat treatment ensures that AISI 4130 attains the desired balance of strength, ductility, and toughness suited for specific applications.

Fabrication Considerations:

AISI 4130 can be welded using most common welding processes such as MIG, TIG, or stick welding. Preheating and post-weld heat treatment are often recommended to prevent cracking and ensure optimal mechanical properties.

Corrosion Resistance

While AISI 4130 offers good corrosion resistance compared to plain carbon steels owing to its chromium content, it is not inherently corrosion-proof. For environments with high exposure to moisture, external coatings or corrosion inhibitors are recommended. When properly treated and maintained, AISI 4130 can perform reliably in various environments.

Advantages of AISI 4130 Steel

The distinct properties of AISI 4130 confer several advantages, making it a preferred choice in multiple industries:

- **High Strength-to-Weight Ratio:** Enables the design of lightweight yet durable structures.
- **Excellent Toughness:** Resists impact and dynamic loading conditions.
- **Good Weldability:** Suitable for complex fabrication and assembly processes.
- **Versability:** Can be heat-treated to achieve various property profiles.
- **Cost-Effective:** Offers a balance of performance and affordability compared to more exotic alloys.

Applications of AISI 4130

Due to its versatile properties, AISI 4130 is extensively used across various sectors:

Aerospace Industry

- Aircraft fuselage frames
- Structural components
- Rocket casings

Automotive Sector

- High-performance chassis parts
- Roll cages
- Racing car frames

Oil & Gas

- Drilling equipment
- Tubing and piping

Sports Equipment

- Bicycle frames
- Motorcycle frames
- Sporting equipment requiring high strength and low weight

Structural and Fabrication

- Construction of bridges, towers, and other load-bearing structures
- Manufacturing of pressure vessels and tooling

Comparison with Other Steel Alloys

AISI 4130 often stands out when compared with other alloy steels due to its optimal properties:

- **Compared to 1020 Carbon Steel:** Higher strength and toughness, better weldability with proper procedures.
- **Compared to 4340 Steel:** Similar strength but with better weldability and corrosion resistance, although 4340 offers higher fatigue strength.
- **Compared to Stainless Steels:** Less corrosion-resistant but more cost-effective and easier to weld.

Common Challenges and Considerations

While AISI 4130 is highly advantageous, certain factors should be considered:

- **Welding Precautions:** Requires preheating and post-weld heat treatment to prevent cracking.
- **Corrosion Susceptibility:** Needs protective coatings or treatments in corrosive environments.
- **Heat Treatment Control:** Precise temperature control is essential to achieve desired properties.

Conclusion

AISI 4130 properties characterized by high strength, toughness, and weldability make it an invaluable material in high-performance applications. Its chemical composition, combined with versatile heat treatment options, allows engineers and manufacturers to tailor its properties for specific needs. Whether used in aerospace, automotive, oil and gas, or structural projects, AISI 4130 continues to demonstrate its reliability and efficiency. Proper handling, treatment, and maintenance further enhance its performance, making it a go-to alloy for demanding engineering challenges.

By understanding its properties and applications, stakeholders can make informed decisions about integrating AISI 4130 into their designs, ensuring safety, durability, and cost-effectiveness.

AISI 4130: An In-Depth Exploration of Its Properties and Applications

Introduction

When it comes to high-performance alloys used across aerospace, automotive, and industrial sectors, AISI 4130 stands out as a versatile and reliable material. Known for its excellent strength-to-weight ratio, weldability, and corrosion resistance, AISI 4130 has become a preferred choice for engineers and manufacturers worldwide. This article provides an expert review of its properties, composition, mechanical characteristics, applications, and factors influencing its performance, offering a comprehensive understanding of this remarkable alloy.

What is AISI 4130?

AISI 4130, also known as chromium-molybdenum steel, is a low-alloy steel classified under the American Iron and Steel Institute (AISI) standards. It is a member of the 4130 family, which is characterized by its controlled alloying elements—mainly chromium and molybdenum—designed to enhance strength, toughness, and weldability.

This steel is renowned for its balanced properties, making it suitable for critical applications where strength, durability, and ease of fabrication are essential. Its chemical composition and heat treatment options allow for tailoring mechanical properties to meet specific engineering requirements.

Chemical Composition of AISI 4130

Understanding the chemical makeup of AISI 4130 is fundamental to appreciating its properties. Its typical composition includes:

Element	Percentage Range	Purpose and Effect
-----	-----	-----
Carbon (C)	0.28% ? 0.33%	Increases strength and hardness; influences weldability
Chromium (Cr)	0.80% ? 1.10%	Adds corrosion resistance and hardenability
Molybdenum (Mo)	0.15% ? 0.25%	Improves strength, toughness, and creep resistance
Manganese (Mn)	0.40% ? 0.60%	Enhances hardenability and tensile strength
Silicon (Si)	Up to 0.35%	Improves strength and oxidation resistance
Other Elements	Trace amounts	Small quantities of sulfur and phosphorus, controlled for quality

The precise control of these elements enables the alloy to deliver a desirable combination of mechanical strength, toughness, and weldability.

Mechanical Properties of AISI 4130

The mechanical properties of AISI 4130 can vary depending on heat treatment, tempering, and manufacturing processes. Nonetheless, standard values provide a useful baseline for understanding its performance.

Tensile Strength

- Range: 75,000 to 110,000 psi (517 to 758 MPa)
- Implication: This high tensile strength allows AISI 4130 to withstand significant loads, making it ideal for structural components, aircraft frames, and automotive chassis.

Yield Strength

- Range: 50,000 to 95,000 psi (345 to 655 MPa)
- Implication: The high yield strength indicates the material's ability to deform elastically under load before permanent deformation, critical for safety and integrity in engineering applications.

Ductility and Toughness

- Elongation: Typically 20% in 2 inches (50 mm)
- Impact Resistance: Good toughness, especially when properly heat-treated, ensuring resilience against sudden shocks or impacts.

Hardness

- Range: Varies based on heat treatment, typically 70-100 HRB in the normalized condition
- Implication: Hardened AISI 4130 can exhibit surface hardness suitable for wear-resistant applications.

Fatigue Strength

- Description: Exhibits excellent fatigue resistance, especially in welded and heat-treated states, essential for cyclic loading environments like aircraft structures and racing cars.

Heat Treatment and Its Effects on Properties

AISI 4130's properties are highly influenced by its heat treatment processes, which include:

- Normalization: Heating to 880-940°C (1600-1720°F) followed by air cooling enhances uniformity and toughness.
- Quenching and Tempering: Heating to around 830-870°C (1525-1600°F), quenching in oil or water, then tempering at 550-700°C (1022-1292°F) increases strength and toughness.
- Austenitizing: Rapid heating to form austenite, followed by rapid cooling, results in a martensitic microstructure with high hardness.
- Stress Relieving: Performed at 500-650°C (932-1202°F) to reduce residual stresses from welding or machining.

The choice of heat treatment directly impacts properties such as hardness, strength, ductility, and weldability, enabling engineers to customize the alloy for specific performance criteria.

Physical Properties of AISI 4130

Understanding its physical characteristics is crucial for designing components and selecting suitable manufacturing processes.

- Density: Approximately 7.85 g/cm³ (0.284 lb/in³)
- Melting Point: Around 1427-1540°C (2599-2800°F)
- Thermal Conductivity: Moderate, approximately 50 W/m·K at room temperature
- Coefficient of Thermal Expansion: 11.7×10^{-6} /°C (from room temperature to 100°C)

These properties influence how the material responds to thermal cycling, welding, and machining.

Corrosion Resistance and Surface Properties

While AISI 4130 possesses some corrosion resistance due to its chromium content, it is not inherently stainless steel. It can form a protective oxide layer, but in aggressive environments, additional surface treatments or coatings are usually necessary.

Common surface treatments include:

- Galvanization
- Nitrocarburizing
- Electropolishing
- Paint or coating applications

Proper maintenance and surface finishing ensure longevity and performance in corrosive environments.

Welding and Fabrication Characteristics

One of AISI 4130's standout features is its excellent weldability, which is vital for building complex structures.

Key considerations for welding include:

- Preheating: Typically 150-250°C (302-482°F) to prevent cracking.
- Post-weld heat treatment: Necessary to relieve stresses and restore mechanical properties.
- Welding methods: Shielded Metal Arc Welding (SMAW), Gas Tungsten Arc Welding (GTAW), and Gas Metal Arc Welding (GMAW) are common.

Advantages in fabrication:

- Good fusion and minimal distortion
- Compatibility with various welding techniques
- Preservation of strength post-welding when proper procedures are followed

Applications of AISI 4130

Thanks to its balanced alloying and properties, AISI 4130 finds diverse applications:

Aerospace Industry

- Aircraft fuselage frames
- Structural components
- Rocket casings

Its strength, lightweight nature, and weldability make it ideal for aerospace structures where weight savings are critical.

Automotive Sector

- Racing car chassis
- High-performance roll cages
- Drive shafts

Its ability to withstand cyclic loads and impact makes it suitable for high-stress environments.

Oil & Gas and Power Generation

- Pipelines
- Pressure vessels
- Turbine components

The alloy's toughness and corrosion resistance (with surface treatment) are advantageous here.

Sporting Equipment

- Bicycle frames
- Motorcycle frames
- Sporting rifles

The high strength-to-weight ratio offers durability without excessive weight.

Factors Influencing the Properties of AISI 4130

Several factors can impact the alloy's performance:

- Heat treatment parameters: Precise control of temperature and cooling rates affects microstructure and mechanical properties.
- Welding procedures: Proper preheat, interpass temperature, and post-weld heat treatment are essential to prevent cracking and maintain strength.
- Microstructure: Fine-grained microstructures exhibit higher toughness and strength.
- Surface finish: Smoother surfaces reduce stress concentrations and corrosion susceptibility.
- Environmental conditions: Exposure to corrosive media necessitates protective coatings or alloy modifications.

Advantages and Limitations

Advantages:

- High strength-to-weight ratio
- Excellent weldability
- Good toughness and ductility
- Versatile heat treatment options
- Resistance to fatigue and impact

Limitations:

- Not inherently corrosion-resistant; requires surface treatments
- Sensitive to improper welding procedures, which can cause cracking

- Moderate machinability compared to non-alloyed steels
- Costlier than mild steels due to alloying elements

Conclusion

AISI 4130 exemplifies a well-balanced low-alloy steel that combines strength, toughness, weldability, and adaptable heat treatment capabilities. Its chemical composition and microstructural characteristics underpin a broad spectrum of applications, particularly where performance and weight considerations are paramount. Understanding its properties in depth allows engineers and manufacturers to optimize design, fabrication, and maintenance processes, ensuring maximum benefits from this versatile alloy.

From aerospace structures demanding high reliability to automotive components requiring lightweight durability, AISI 4130 remains a cornerstone material in advanced engineering. Proper handling, heat treatment, and surface management unlock its full potential, making it a staple in industries that push the boundaries of material performance.

References

- ASTM A519 / A519M ? Standard Specification for Steel Mechanical Tubing
- ASM Metals Handbook, Volume 1: Properties and Selection: Steel, Aluminum, Copper, Nickel, and Titanium Alloys
- "Steel Heat Treatment and Processing,"

Question What are the key mechanical properties of AISI 4130 steel? AISI 4130 steel exhibits high strength, good toughness, and excellent weldability, with a typical tensile strength ranging from 70,000 to 100,000 psi (480 to 690 MPa) depending on heat treatment. How does heat treatment affect the properties of AISI 4130? Heat treatment, such as annealing, normalizing, or quenching and tempering, can significantly enhance the hardness, strength, and ductility of AISI 4130, making it suitable for various structural and aerospace applications. Is AISI 4130 weldable and what precautions should be taken? Yes, AISI 4130 is highly weldable. To prevent weld cracking and maintain properties, preheating, controlled cooling, and proper welding techniques should be used, especially when welding thick sections. What are the common applications of AISI 4130 steel? AISI 4130 is widely used in aerospace, automotive, oil and gas, and structural applications due to its strength-to-weight ratio, weldability, and toughness. How does corrosion resistance of AISI 4130 compare to other steels? AISI 4130 has moderate corrosion resistance but is not inherently corrosion-proof. It often requires coatings or treatments, such as painting or plating, for applications exposed to corrosive environments. What are the typical chemical composition elements in AISI 4130? AISI 4130 primarily contains carbon (around 0.28-0.33%), chromium (0.80-1.10%), molybdenum (0.15-0.25%), along with small amounts of manganese, silicon, and iron, which

contribute to its properties. Can AISI 4130 be used in high-temperature environments? While AISI 4130 maintains strength at elevated temperatures, its maximum service temperature is generally around 600°C (1112°F). For extremely high-temperature applications, specialized alloys are recommended.

Related keywords: aisi 4130 properties, 4130 steel alloy, chromoly steel characteristics, aisi 4130 composition, 4130 steel tensile strength, aisi 4130 hardness, 4130 steel weldability, aisi 4130 applications, 4130 steel corrosion resistance, aisi 4130 thermal properties

Scm435 equivalent astm

scm435 equivalent astm refers to the standards and specifications that align SCM435 alloy steel with ASTM (American Society for Testing and Materials) standards. SCM435 is a popular alloy steel known for its excellent strength, toughness, and wear resistance, making it a preferred choice in heavy-duty engineering applications such as machinery parts, shafts, gears, and high-stress components. When sourcing materials internationally, especially in regions where ASTM standards are prevalent, understanding the equivalents of SCM435 according to ASTM standards is crucial for ensuring compatibility, quality, and performance.

In this comprehensive guide, we explore the details of SCM435 and its ASTM equivalents, key specifications, applications, and how to select the right material for your engineering needs. Whether you are a procurement manager, engineer, or manufacturer, this article aims to provide valuable insights into the equivalency of SCM435 and ASTM standards.

Understanding SCM435 Steel

What is SCM435 Steel?

SCM435 is a medium alloy structural steel grade primarily composed of carbon, manganese, and other alloying elements such as chromium and molybdenum. It is produced through hot forging and heat treatment processes to achieve high tensile strength and toughness. This steel is often used in manufacturing parts that require high fatigue strength, wear resistance, and good machinability.

Key characteristics of SCM435 include:

- High tensile strength
- Good toughness and ductility

- Excellent weldability
- Good wear resistance
- Suitable for heat treatment to enhance mechanical properties

Common Applications of SCM435

Due to its versatile properties, SCM435 is widely used in various industries:

- Automotive components: gears, shafts, axles
- Heavy machinery parts
- Hydraulic equipment
- Structural components subjected to heavy loads
- Forged parts requiring high strength and toughness

ASTM Standards and Steel Equivalents

Understanding ASTM Steel Standards

ASTM International develops and publishes technical standards for a wide range of materials, including various grades of steel. These standards specify chemical compositions, mechanical properties, testing methods, and other requirements to ensure material quality and consistency.

Some common ASTM steel standards relevant to alloy steels include:

- ASTM A29 (Standard Specification for Steel Bars, Alloy, Standard, for General Use)
- ASTM A193/A193M (Standard Specification for Alloy Steel and Stainless Steel Bolting Materials)
- ASTM A182 (Standard Specification for Forged or Rolled Alloy and Stainless Steel Pipe Flanges, Forged Fittings, and Valves and Parts)
- ASTM A320 (Standard Specification for Alloy Steel Bolting Materials for Low-Temperature Service)

Among these, ASTM A29 is particularly significant when discussing steel material grades comparable to SCM435.

ASTM Equivalent Grades to SCM435

While SCM435 is a Japanese steel grade (JIS G4103), several ASTM standards specify alloy steels with similar chemical compositions and mechanical properties. The most relevant ASTM equivalent

to SCM435 is:

ASTM A29 (Grade 4140 or 4140H)

Why ASTM A29 Grade 4140/4140H?

- Chemical Composition: Similar levels of chromium, molybdenum, and carbon.
- Mechanical Properties: Comparable tensile strength, toughness, and hardenability.
- Application: Both are used for similar high-stress components.

Other ASTM grades that are sometimes considered equivalents, depending on specific mechanical and chemical requirements, include:

- ASTM A322 Grade 4140
- ASTM A193 B7 (for bolting applications)
- ASTM A193 B7M (corrosion-resistant version)

It's essential to compare chemical compositions and mechanical properties in detail to confirm equivalency for your specific application.

Comparative Chemical Composition

Element	SCM435 (%)	ASTM A29 Grade 4140 (%)	Notes
--- --- --- ---			
Carbon (C)	0.38 - 0.43	0.37 - 0.43	Similar carbon content for good strength and weldability
Manganese (Mn)	0.60 - 0.90	0.60 - 0.90	Enhances hardenability and strength
Chromium (Cr)	0.80 - 1.10	0.80 - 1.10	Improves corrosion resistance and hardness
Molybdenum (Mo)	0.15 - 0.30	0.15 - 0.30	Adds toughness and high-temperature strength
Nickel (Ni)	Trace	Trace	Present in small quantities

Note: Exact compositions can vary slightly depending on the manufacturer and specific grade.

Mechanical Properties and Heat Treatment

Mechanical Properties of SCM435 and ASTM A29 Grade 4140

| Property | SCM435 | ASTM A29 Grade 4140 | Typical Values |

|---|---|---|---|

| Tensile Strength | 680 - 950 MPa | 655 - 885 MPa | After heat treatment |

| Hardness (HRC) | 20 - 30 (annealed) | 20 - 30 | Depending on heat treatment |

| Toughness | High | High | Suitable for heavy-duty applications |

| Wear Resistance | Excellent | Good | Enhances durability |

Heat Treatment Processes

Both SCM435 and ASTM 4140 can undergo various heat treatment processes to optimize properties:

- Quenching and Tempering: To achieve high strength and toughness.
- Normalizing: To refine grain size and improve machinability.
- Precipitation Hardening: For specific applications requiring increased hardness.

Proper heat treatment ensures the alloy steels meet the required mechanical properties for their intended applications.

Key Factors to Consider When Choosing an ASTM Equivalent

When selecting an ASTM standard or grade equivalent to SCM435, consider the following factors:

- Chemical Composition: Ensure the alloying elements match or are within acceptable ranges.
- Mechanical Properties: Check tensile strength, toughness, and hardness requirements.
- Application Requirements: Consider the operating environment, load conditions, and wear resistance.
- Heat Treatment Compatibility: Confirm that the steel grade can be processed to meet your specifications.
- Availability and Cost: Verify the availability of materials and associated costs.
- Certification and Standards Compliance: Ensure suppliers provide proper certification matching ASTM standards.

Applications of ASTM A29 Grade 4140 as SCM435 Equivalent

ASTM A29 Grade 4140 is widely used in applications similar to SCM435:

- Automotive transmission gears
- Hydraulic cylinders
- Structural components subjected to high stress
- Oil and gas industry equipment
- Heavy-duty machinery parts

The compatibility of this grade with SCM435 makes it a popular choice for international procurement and manufacturing.

Conclusion: Ensuring Material Compatibility

Understanding the ASTM equivalents of SCM435 is vital for engineers and manufacturers working across international borders. ASTM A29 Grade 4140, among others, is a close match in chemical composition and mechanical properties, making it the most commonly accepted ASTM equivalent. However, always verify specific requirements through detailed chemical analysis and mechanical testing.

By carefully comparing standards, properties, and application needs, you can select the most suitable alloy steel grade, ensuring optimal performance, durability, and cost-effectiveness in your projects.

Additional Resources

- ASTM International official website: [www.astm.org](<https://www.astm.org>)
- JIS G4103 standards for SCM435
- Steel supplier catalogs and technical datasheets
- Metallurgical consultants for detailed material analysis

In summary, choosing the correct ASTM equivalent for SCM435 involves understanding the chemical and mechanical similarities, application requirements, and available standards. ASTM A29 Grade 4140 remains the most recognized counterpart, ensuring you meet international quality standards and achieve reliable performance in your engineering projects.

scm435 equivalent astm: An In-Depth Look at Material Standards and Equivalencies

In the world of engineering and manufacturing, selecting the right material is crucial to ensure the durability, strength, and performance of components and structures. Among the many alloy options available, SCM435 stands out for its excellent toughness, hardenability, and overall versatility. However, when working across different standards and specifications, understanding the equivalents of SCM435 in other international standards becomes essential. This article delves into the details of scm435 equivalent astm, exploring its composition, properties, and the standards that align with it, providing engineers and manufacturers with a comprehensive guide to make informed material choices.

Understanding SCM435: An Overview

What is SCM435?

SCM435 is a medium-carbon alloy steel primarily used in the manufacturing of gears, axles, shafts, and other mechanical parts requiring high strength and toughness. Originating from the Japanese steel classification system, SCM435 is part of the "Steel for Machine Structural Use" (denoted by "SC") series. Its composition typically includes:

- Carbon (C): 0.40% ? 0.48%
- Manganese (Mn): 0.60% ? 0.90%
- Silicon (Si): up to 0.40%
- Chromium (Cr): 0.80% ? 1.10%
- Molybdenum (Mo): 0.15% ? 0.30%

This combination provides excellent hardenability, strength, and wear resistance, making it suitable for heat-treated parts.

Mechanical Properties and Applications

SCM435 offers:

- Tensile strength: up to 850-950 MPa after heat treatment
- Hardness: can reach 50-60 HRC depending on tempering
- Good toughness and ductility

Common applications include:

- Gears and gear shafts

- Crankshafts
- Axles
- Heavy-duty mechanical components

Understanding these properties is vital when comparing SCM435 with its equivalents in other standards.

International Standards and SCM435: The Need for Equivalence

The Importance of Standard Equivalents

While SCM435 is a well-established Japanese standard, global manufacturing often demands compliance with other standards such as ASTM (American Society for Testing and Materials), DIN (German Institute for Standardization), or EN (European Norms). Recognizing equivalent materials ensures consistent quality, performance, and compliance across international markets.

Challenges in Finding Equivalents

Differences in chemical compositions, heat treatment procedures, and testing methods can make direct equivalence challenging. Therefore, manufacturers and engineers rely on chemical composition ranges, mechanical properties, and heat treatment guidelines to identify suitable substitutes.

ASTM Standards and Material Equivalents to SCM435

The ASTM A29/A29M Standard: High-Strength Alloy Steels

ASTM A29/A29M covers various grades of alloy steels, including those suitable for heat treatment and mechanical applications.

Key ASTM Grades Equivalent to SCM435:

- ASTM 4140 (Chrome-Molybdenum Steel)
- Composition: Similar to SCM435, with chromium and molybdenum additions
- Typical Composition:
 - Carbon: 0.38% ? 0.43%
 - Manganese: 0.75% ? 1.00%
 - Chromium: 0.80% ? 1.10%
 - Molybdenum: 0.15% ? 0.25%
- Mechanical Properties: Tensile strength up to 930 MPa after heat treatment

- ASTM 4142 (Chrome-Molybdenum Steel)
- Slightly higher alloy content, used for similar applications

Comparison Table: ASTM 4140 vs SCM435

Property	SCM435	ASTM 4140
Carbon	0.40?0.48%	0.38?0.43%
Manganese	0.60?0.90%	0.75?1.00%
Chromium	0.80?1.10%	0.80?1.10%
Molybdenum	0.15?0.30%	0.15?0.25%
Tensile Strength	850?950 MPa	Up to 930 MPa

This similarity indicates ASTM 4140 as a close equivalent for SCM435 in many applications.

The ASTM A29/A29M Specification: Heat-Treatable Alloy Steels

ASTM A29 grades, especially 4140 and 4130, are often used as equivalents to SCM435, especially when heat treatment and mechanical properties are critical.

Other Relevant ASTM Grades

- ASTM 4340: Known for higher toughness and strength, suitable where additional strength is needed.
- ASTM 4150: Offers similar properties but with different alloying specifics.

Comparing Chemical Composition and Mechanical Properties

Chemical Composition

Element	SCM435 Range	ASTM 4140 Range	Notes

| Carbon | 0.40?0.48% | 0.38?0.43% | Slight variation; both suitable for heat treatment |

| Manganese | 0.60?0.90% | 0.75?1.00% | Similar, enhances hardenability |

| Chromium | 0.80?1.10% | 0.80?1.10% | Identical; improves corrosion resistance and hardness |

| Molybdenum | 0.15?0.30% | 0.15?0.25% | Similar, contributes to strength |

Mechanical Properties

- Tensile strength: Both materials can achieve approximately 850?950 MPa after proper heat treatment.
- Hardness: Can reach 50?60 HRC, suitable for wear-resistant applications.
- Toughness: Maintained through appropriate heat treatment processes.

Heat Treatment and Processing

Both SCM435 and ASTM 4140 respond well to quenching and tempering, allowing customization of properties based on application needs.

Practical Considerations When Using ASTM Equivalents

Material Selection

- Application-specific requirements: Ensure that the mechanical properties, corrosion resistance, and machinability meet the application's demands.
- Availability: ASTM 4140 is widely available in North America, making it a practical choice for international projects.

Certification and Testing

- Always verify material certifications to confirm chemical composition and mechanical properties.
- Conduct additional testing if necessary, especially for critical components.

Cost and Supply Chain

- Consider manufacturing lead times and costs associated with different standards.

- International suppliers often stock ASTM 4140, making logistics smoother.

Summary of Key Takeaways

- SCM435 is a Japanese alloy steel renowned for its strength, toughness, and versatility, suitable for heat-treated mechanical parts.
- ASTM 4140 is the most common equivalent in the ASTM standard, sharing similar chemical composition and mechanical properties.
- Both materials are suitable for applications requiring high hardness, wear resistance, and toughness, such as gears, shafts, and axles.
- Proper heat treatment is essential to harness the full potential of these alloys.
- Always verify certifications and conduct testing when substituting materials across standards to ensure compliance and performance.

Final Thoughts

Understanding the equivalency between SCM435 and ASTM standards like ASTM 4140 empowers engineers, manufacturers, and procurement specialists to make informed decisions in global supply chains. While differences in standards can pose challenges, a detailed comparison of chemical compositions, mechanical properties, and intended applications ensures that the right material is chosen for the job. Whether producing high-performance gears or heavy-duty shafts, recognizing these equivalents helps maintain quality, consistency, and reliability across international markets.

In an increasingly interconnected world, mastering scm435 equivalent astm standards is not just about compliance?it's about optimizing performance, reducing costs, and ensuring the longevity of engineered components.

Question What is the ASTM equivalent of SCM435 steel? The ASTM equivalent of SCM435 steel is AISI 4340, which is a low alloy steel known for its toughness and strength. How does SCM435 compare to ASTM AISI 4340? SCM435 and ASTM AISI 4340 are similar in composition and mechanical properties, with SCM435 being the Japanese designation and AISI 4340 the North American standard. Can I use ASTM AISI 4340 as a substitute for SCM435 in engineering applications? Yes, ASTM AISI 4340 is commonly used as a substitute for SCM435 due to their comparable alloy compositions and mechanical performance. What are the main properties of SCM435 and its ASTM equivalent? Both SCM435 and ASTM AISI 4340 exhibit high strength, toughness, good ductility, and excellent weldability, making them suitable for high-stress components. Is there a difference in heat treatment between SCM435 and ASTM AISI 4340? The heat treatment processes for SCM435 and ASTM AISI 4340 are similar, typically involving quenching and tempering to achieve desired mechanical properties. Where can I find the detailed chemical composition of SCM435 and its ASTM equivalent? Detailed chemical composition charts

can be found in Japanese Industrial Standards (JIS) for SCM435 and ASTM standards for AISI 4340, available in technical datasheets and standards documentation. Are there any differences in corrosion resistance between SCM435 and ASTM AISI 4340? Both steels have similar corrosion resistance, but proper surface treatment and protective coatings are recommended to enhance corrosion protection. What industries commonly use SCM435 and its ASTM equivalent? Both steels are widely used in automotive, aerospace, machinery, and structural applications where high strength and toughness are required.

Related keywords: SCM435, ASTM, alloy steel, quenched and tempered steel, 1.7131, 42CrMo4, 42CrMoS4, steel grade, heat-treated steel, alloy steel standards